

RECEIVED
CENTRAL FAX CENTER

MAR 17 2008

In the Claims:

Kindly amend the claims as follows:

1. (Currently amended) A method for manufacturing an anisotropic conductive sheet comprising:

step A; etching through a monocrystal silicon wafer by a deep reactive ion etching so as to form a part having a bending leaf spring shape such that planes of said formed leaf spring are parallel to a cross section of said wafer,

step B; forming a silicon spring electrode by forming a conductive layer on a surface of said part having the bending leaf spring shape formed in step A, and

step C; inserting a plurality of said silicon spring electrodes formed in step B respectively into through holes of a soft plastic sheet such that said spring electrodes are clamped and fixed to said soft plastic sheet and do not extend out of the holes during operation.